

# 22-1250M

22 Line HS 2K Topcoat 22-1250-M



A brand of BASF –  
We create chemistry

<b>Application:</b>	Mat direct gloss HS solid-colour topcoat
<b>Key Features:</b>	High solids content; efficient; outstanding weathering resistance, yellowing resistance and hardness; very good curing; very good build
<b>Remarks:</b>	<ul style="list-style-type: none"> <li>• Select hardener according to ambient temperature and size of object to be painted.</li> <li>• Also for use on plastics, without the need to add Glasurit 522-111 Softface Additive.</li> <li>• <b>Do not mix with 522-M 0 and 522-MC 35 Mixing Clear or 22 VOC MC600.</b></li> </ul>

**2:1+10 %****Mixing Ratio**

100 % by volume

22-1250M

**Hardener**

50 % by volume

929-91

**Reducer**

10 % by volume

**Spray viscosity at 20°C**

DIN 4:

20-24 s

**Potlife at 20°C**

1 h

**Application:****Compliant gravity-feed  
spray gun****HVLP spray gun****Application pressure** bar

2

2-3

**Nozzle pressure** bar

0.7

**Nozzle size**

1.3-1.4

1.3

**Number of spray coats**

2

**Flash off at 20°C** min

Flash off until matt after each spraycoat and before baking.

**Film thickness**

µm

50-70

**Safety advice:**

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

**2004/42/IIIB(e)(840)839:** The EU limit value for this product ( product category: IIB.e ) in ready to use form is max 840 g/litre of VOC. The VOC content of this product is 839 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH - Automotive Refinish Coatings Solutions Europe - Glasuritstrasse 1 - 48165 Münster - Germany

11/2022

# 22-1250M

22 Line HS 2K Topcoat 22-1250-M



A brand of BASF –  
We create chemistry



**Drying at 20°C**

8 h

**Drying at 60°C**

30 min

---

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

---

## Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

**2004/42/IIIB(e)(840)839:** The EU limit value for this product ( product category: IIB.e ) in ready to use form is max 840 g/litre of VOC. The VOC content of this product is 839 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at [www.glasurit.com](http://www.glasurit.com) or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

BASF Coatings GmbH - Automotive Refinish Coatings Solutions Europe - Glasuritstrasse 1 - 48165 Münster - Germany

11/2022