

925-2002

HS clear ultra scratch resistant



A brand of BASF –
We create chemistry

- Application:** Ultra scratch-resistant HS clear for 90 Line basecoat / clearcoat systems.
- Key Features:** High solids content; ultra scratch-resistant; long-term gloss retention, outstanding weathering resistance, excellent finish quality, very quickly ready for polishing.
- Remarks:**
- Suitable for repairing ultra scratch-resistant original finishes.
 - Select reducer according to ambient temperature and size of object to be painted.
 - When using 925-2002 on 55 Line basecoats, add 3% by weight of 929-93 to 55 Line mixing bases.



Spreading rate 335 m²/l at 1 µm

100 % by weight+40 % by weight+20 % by weight



Mixing Ratio 925-2002



Hardener 929-2002



Reducer 352-91, -216, -370



Spray viscosity at 20°C DIN 4: 20-22 s **Potlife at 20°C** 1 h

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(e)(840)419: The EU limit value for this product (product category: IIB.e) in ready to use form is max 840 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.

925-2002

HS clear ultra scratch resistant



A brand of BASF –
We create chemistry

Application:	 Compliant gravity-feed spray gun	 HVLP spray gun
Application pressure	bar	2
Nozzle pressure	bar	0.7
Nozzle size		1.3-1.4
Number of spray coats		2
Flash off at 20°C	min	3-5
Film thickness	µm	40-60



Drying at 60°C 40 min



Infrared (short wave) 10 min

Infrared (medium wave) 10-15 min

Please note: For automotive refinish, repair instructions of vehicle manufacturers, in particular regarding installed sensor technology, must always be observed in addition to the processing instructions given within this document.

Safety advice:

The products are suitable for professional use only.

It cannot be ruled out that this product contains particles < 0.1 µm.

2004/42/IIIB(e)(840)419: The EU limit value for this product (product category: IIB.e) in ready to use form is max 840 g/litre of VOC. The VOC content of this product is 419 g/litres.

The data contained in this publication are based on our current knowledge and experience. In view of the many factors that may affect processing and application of our products, these data do not relieve processors from carrying out their own investigations and tests; neither do these data imply any guarantee of certain properties, nor the suitability of the products for a specific purpose. Any descriptions, drawings, photographs, data, proportions, weights etc. given herein are for general information purpose only; they may change without prior information and do not constitute the agreed contractual quality of the products (product specification). The latest version supersedes all previous versions. You can obtain the latest version from our website at www.glasurit.com or directly from your sales partner. It is the responsibility of the recipient of our products to ensure that any proprietary rights and existing laws and legislation are observed.